


Moso® Solid Joist

Product

The MOSO solid joist consists of 3 layers of bamboo (side pressed style). The joist has numerous applications, but is mostly applied as raw material for banisters (for which the material is being round milled).



Solid joist side pressed

Product line

Code Natural	Code Caramel	Style	Thickness (mm)	Type	Construction (mm)	Dimensions (mm)
BL-200	BL-250	SP	55	3 ply	3x18,3	2440x55

SP = Side pressed

Technical characteristics

- Hardness: 4,0 kg/mm² (Brinell)
- Shrink/swell: 0,14% per 1% change in moisture content
- Equilibrium MC: 10% at 20 °C and 65% Rel. Air Humidity
8% at 20 °C and 50% Rel. Air Humidity
- Density: 700 kg/ m³
- Glue: D3 water resistant
- Fire resistance: EN 13501-1: Cfl-s1
- Emission formaldehyde: <0,124 mg/m³ (E1 norm)